

Annexe A2 - 18

Joint hydrogonflant



Product Description	Requirements	Offer															
Chemical Basis	Acrylate-based polymer																
Packaging	Rolls packed in cartons																
Aspect/color	Red expansion profile. Right: red original rectangular profile. Left: expanded profile.																
Shelf life	In original, unopened packaging: 36 months from production date																
Storage Conditions	Store at temperatures between 5 and 35 degrees. Store in a dry place, protected from UV rays																
Dimensions	<table border="1"> <thead> <tr> <th>Type</th><th>Width</th><th>Thickness</th></tr> </thead> <tbody> <tr> <td>SikaSwell® A 2005</td><td>20 mm</td><td>5 mm</td></tr> <tr> <td>SikaSwell® A 2010</td><td>20 mm</td><td>10 mm</td></tr> <tr> <td>SikaSwell® A 2025</td><td>20 mm</td><td>25 mm</td></tr> </tbody> </table>	Type	Width	Thickness	SikaSwell® A 2005	20 mm	5 mm	SikaSwell® A 2010	20 mm	10 mm	SikaSwell® A 2025	20 mm	25 mm				
Type	Width	Thickness															
SikaSwell® A 2005	20 mm	5 mm															
SikaSwell® A 2010	20 mm	10 mm															
SikaSwell® A 2025	20 mm	25 mm															
Volume Change																	
Swelling	<table border="1"> <thead> <tr> <th>Time</th><th>Demineralized water</th><th>Saline solution at 5%</th></tr> </thead> <tbody> <tr> <td>3 jours</td><td>~100 %</td><td>~60 %</td></tr> <tr> <td>7 jours</td><td>~150 %</td><td>~100 %</td></tr> <tr> <td>14 jours</td><td>~200 %</td><td>~120 %</td></tr> <tr> <td>21 jours</td><td>~220 %</td><td>~140 %</td></tr> </tbody> </table>	Time	Demineralized water	Saline solution at 5%	3 jours	~100 %	~60 %	7 jours	~150 %	~100 %	14 jours	~200 %	~120 %	21 jours	~220 %	~140 %	
Time	Demineralized water	Saline solution at 5%															
3 jours	~100 %	~60 %															
7 jours	~150 %	~100 %															
14 jours	~200 %	~120 %															
21 jours	~220 %	~140 %															
Swelling pressure	After 3 days storage in tap water ≤ 16bars																
Operating Temperature	0°C min./ +50°C max																
Application Information																	
Substrate humidity	the substrate must be clean, dry, at most damp-matt, free from friable particles, dust, cement laitance, gravel nests, release agents, rust and impurities.																
Ambient air temperature	+5°C minimum																
Substrate temperature	+5°C minimum																